

ABSTRACT

*Sub C1*

The process for producing a polymeric actuator according to the invention is a process for producing a polymeric actuator comprising an ion-exchange resin product and metal electrodes which are formed on the surface of the ion-exchange resin product and are insulated from each other and functioning as an actuator by applying a potential difference between the metal electrodes in such a state that the ion-exchange resin product contains water to allow the ion-exchange resin product to undergo bending or deformation, wherein the following steps (i) to (iii) are repeatedly conducted to form the metal electrodes ranging from the surface of the ion-exchange resin product to the inside thereof;

10 (i) a step of allowing the ion-exchange resin product to adsorb a metal complex (adsorption step), (ii) a step of reducing the metal complex adsorbed on the ion-exchange resin product by a reducing agent to deposit a metal on the surface of the ion-exchange resin product

15 (deposition step), and (iii) a step of washing the ion-exchange resin product having the deposited metal (washing step). By the formation of metal electrodes through the above steps, a polymeric actuator having simple structure, capable of being easily miniaturized,

032535 032536 032537 032538 032539 032540

showing quick response and capable of generating large displacement can be obtained.

The polymeric actuator 1 of the invention comprises an ion-exchange resin product 2 in the form of a slender rectangular flat sheet and metal electrodes 3a, 3b which are formed on the surface of the ion-exchange resin product 2 and are insulated from each other, and the polymeric actuator is designed so that the ion-exchange resin product 2 undergoes bending or deformation by applying a potential difference between the metal electrodes in such a state that the ion-exchange resin product contains an alkylammonium ion-containing aqueous solution. This polymeric actuator has excellent flexibility, is lightweight, has quick response and is capable of generating large displacement.

092363638-022630